

지능재료 및 설계 과제물 1번

제출기한: 3월 30일 (금)

1.

- a) Using the information in the attached Table, find the weight-based figures of merit (specific strength, specific stiffness) for these materials. Plot the specific strength in both tension and compression versus the specific stiffness for these materials.
- b) Using the following cost data, determine cost-based figures of merit (specific cost) for these materials. Plot the cost figure of merit versus the weight figure of merit for the the three cases of: tensile stiffness, tensile strength and compressive strength.

Material	Cost per pound
1. 2024-T3 Aluminum	\$2.00
2. 7075-T6 Aluminum	\$2.00
3. 7175-T73 Aluminum	\$3.00
4. Ti6Al-4V Titanium	\$14.00
5. 300M Steel	\$1.00
6. AISI 4130 Steel	\$0.25
7. Typical Graphite/Epoxy	\$40.00

- c) What does all this information suggest about the use of these materials?

COMPARISON OF G/E WITH A FEW METAL ALLOYS

	Tensile Ult [MPa]	Compress Yield [MPa]	Modulus GPa	Specific Gravity
2024-T3 Aluminum	462	290	74	2.77
7075-T6 Aluminum	586	531	72	2.80
7175-T73 Aluminum	504	436	70	2.80
Ti6Al-4V Titanium	923	909	110	4.43
300M Steel	1931	1703	200	7.84
AISI 4130 Steel	655	517	200	7.84
G/E ($V_F = .60$)	1661	1698	130	1.61

2.

Given a Weibull distribution with a scale factor $\beta = 4770$ and a shape factor $\alpha = 6.4$. Plot the probability density distribution $p(x)$ versus x and the cumulative probability $P(x)$ versus x on linear scales for $x = 0$ to 8000 .

$$p(x) = \frac{\alpha}{\beta} \left(\frac{x}{\beta}\right)^{\alpha-1} e^{-\left(\frac{x}{\beta}\right)^\alpha}$$

$$P(x) = 1 - e^{-\left(\frac{x}{\beta}\right)^\alpha}$$

3.

Given the fiber and matrix data, $E_{Tf} = 2.3$ Msi, $E_m = 0.5$ Msi
Plot families of E_T vs. V_f (transverse composite stiffness vs. fiber volume fraction) curves, using

a) the mixed series-parallel model with $\eta = 0, .25, .50, .75, 1.0$

b) the Chamis model
$$E_T = 1 / \left(\frac{1 - \sqrt{V_f}}{E_m} + \frac{\sqrt{V_f}}{E_{Tf}} \right)$$

4.

How does the following fictitious experimental data fit on these curves?

V_f	.5	.55	.6	.65	.7
E_T (Msi)	1.12	1.22	1.26	1.35	1.40

5.

Given the following constituent data

	Fiber	Matrix
E_L (Msi)	34.0	.5
E_{Tf} (Msi)	2.3	.5
G_{LTf} (Msi)	2.9	.19
ν_{LT}	.27	.35
α_L ($\mu\epsilon/ F$)	-7.55	32.0

Make a simple estimate of the overall composite properties E_L , E_T , G_{LT} , ν_{LT} , α_L for fiber volume fractions $V_f = .5, .6, .7$